
VIEROPAINT FONDO

Viero

www.vieropaints.com

info@vieropaints.it

Product data sheet: VID455168T

Rev. 01 dated 31/07/2018

Name	VIEROPAINT FONDO
Description	Extreme-filling strength matt paint.
Product characteristics	VIEROPAINT FONDO is a very easy to wash, masking and extremely matt paint that is ideal as a base for smooth decorative effects and as a coloured base for glazing.
VOC Classification (Volatile organic compounds) Directive 2004/42/EC IAQ Class (Indoor Air Quality)	Matt paints for interior walls and ceilings. EU limit value of VOC for VIEROPAINT FONDO (cat. A/a): 30 g/L (2010). VIEROPAINT FONDO contains no more than 30 g/L of VOC.  <small>*ISO 16000/AFFSET</small>
Produced in	MADE IN ITALY
Main application tools	Roller, brush
Achievable effects Application method	For unpainted walls (newly set float finish plasters, prefabricated panels, new plasterboard or sheet rock): If surfaces are not particularly absorbent, directly apply 1 or 2 coats of VIEROPAINT FONDO. For walls painted with tempera paint: If the surface is not particularly powdery, thoroughly clean the surface, stucco over any imperfections with STUCCO FONDO, and then sand and clean away dust. Directly apply 1 or 2 coats of VIEROPAINT FONDO. For powdery tempera painted surfaces, strip away the tempera layer and then apply 1 coat of water-based PRIMER ALTA PENETRAZIONE fixative. Allow to dry for 6-12 hours, and then apply 1 or 2 coats of VIEROPAINT FONDO. For walls painted with washable paints: Thoroughly clean the surface, stucco over any imperfections with STUCCO FONDO, and then sand and clean away dust. Then directly apply 1 or 2 coats of VIEROPAINT FONDO.
Practical tips	The base coat should be set, clean and free from any chipping, peeling and/or dampness. New plasters should be left to age for at least 4-5 weeks to allow for complete carbonation. Environmental conditions -> temperature: min. + 5 °C/max. + 35 °C, relative humidity: < 75%. Primer conditions -> temperature: min. + 5 °C/max. + 35 °C, humidity: < 10 with respect to relative humidity. Shake the product before use or, if it is very dense, use a spatula or a mixing drill to achieve a workable consistency. It is recommended that the colour of the completely dried product be checked before application.

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

VIEROPAINT FONDO



www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455168T
Rev. 01 dated 31/07/2018

Do not apply the product on surfaces exposed to direct sunlight or in the presence of strong drafts.
Do not rework on the same surface.
Do not interrupt application in the middle of a wall.
The product may not be stored for more than 48 hours after dilution.
Rinse used tools with water immediately after use.
Keep the paint can sealed and away from freezing temperatures and sunlight.

Safety precautions

Safety information for users is contained in the relative safety data sheet.
Empty containers or containers with traces of dried product film should be disposed of according to local regulations.

FOR PROFESSIONAL USE ONLY

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

VIEROPAINT FONDO



www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455168T
Rev. 01 dated 31/07/2018

TECHNICAL/REGULATORY INFORMATION	APPLICABLE REGULATION	INFO AT 20 °C AND 60% HUMIDITY
Appearance in the can Finish appearance		Dense liquid Matt
Density g/ml	UNI 8910	1,29 ÷ 1,52
Brookfield Viscosity cPs	ASTM D 2196	5000 ÷ 14000
Natural spread rate (lt/m ²) per coat	ISO 7254	0.15 – 0.20 depending on the surface absorption strength
Flash point °C	UNI 8909	Non-flammable
Shelf life (in a cool and dry place)	UNI 10154.	At least 24 months
Dry to touch Hours (h)		Max.: 1
Hard dry Hours (h)		Max.: 24
Overcoating Hours (h)		4 ÷ 6
Application places		Interiors
Base + achievable colours		White, Medium, Neutral + Archideco Bright colour palette
Binder		Vinyl versatate
Tool cleaning		Water
Dilution % by volume		10 ÷ 20% Up to 10% for colours made from a neutral base

FOR PROFESSIONAL USE ONLY

Toll Free Number: 800.219.420 (Italy)
International assistance: +39.0583.2424 (from other countries)

Mon - Fri [8:00 am/1:00 pm - 2:00 pm/5:30 pm]



CROMOLOGY
Italia

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =
= ISO 14001 =
= OHSAS 18001 =

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424