
RASA LIME



www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455174T
Rev. 01 dated 31/07/2018

Name	RASA LIME
Description	Smoothing lime putty-base powder
CLASSIFICATION (UNI EN 998-1)	Technical details regarding masonry mortars: part n. 1: mortars for interior and exterior plasters; mortars for general purposes (GP); conformity certification system: 4
Classification (UNI EN 1062-1)	G0 E5 S3 V1 W2 A0 C0
Produced in	MADE IN ITALY
Main application tools	Steel trowel, sponge trowel
Achievable effects	For new and set (mineral) plasters: thoroughly clean the surface, removing dust, dirt, debris, and any loose plaster fragments. Ensure that the wall is perfectly dry and, on highly absorbent surfaces, apply a smooth, base-rendering coat of PRIMER ALTA PROTEZIONE adhesive primer.
Application method	<p>For previously painted or partially deteriorated (mineral) plasters:</p> <ul style="list-style-type: none">– remove any trace of dirt, loose parts or deposits;– For old paint: use a paint stripper and wash the surface with a steam cleaner. In the event of mould, treat the surface with an anti-mould solution. <p>Perform any stuccoing of thicknesses up to 5 mm with RASA LIME after reinforcing and smoothing with PRIMER ALTA PENETRAZIONE adhesive primer and allow to set for at least 5 ÷ 6 days. Greater thicknesses should be treated using materials compatible with the existing plaster and allowed to set.</p> <p>Apply RASA LIME with a stainless steel trowel onto the desired surface and smooth out using the same tool; before it begins to harden, use a sponge trowel to achieve a float finish.</p>
Practical tips	<p>Do not apply the product on surfaces exposed to direct sunlight or in the presence of strong drafts. The base coat should be set, clean and free from any chipping, peeling and/or dampness. New plasters should be left to age for at least 4-5 weeks to allow for complete carbonation. For exterior applications, the primer should be a lime putty-base mineral coating that is moist enough for proper adhesion. If using a non-lime putty based primer, ensure adequate smoothing with RASALIME.</p> <p>Environmental conditions -> temperature: min. + 5 °C/max. + 35 °C, relative humidity: < 75%. Primer conditions -> temperature: min. + 5 °C/max. + 35 °C, humidity: < 10 with respect to relative humidity.</p> <p>Mix ADESAN LIME with 25% water to achieve a uniform paste, making sure to prevent the formation of any clots. Wait 15 minutes before applying. The mixture will remain usable for about 2 hours. After exterior applications, surfaces should be protected against driving rain, freezing temperatures (temp > 5 °C), fog, dew, and dust for at least 48 hours.</p> <p>Rinse used tools with water immediately after use.</p> <p>Keep the paint can sealed and away from freezing temperatures and sunlight.</p>

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

RASA LIME



www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455174T
Rev. 01 dated 31/07/2018

Safety precautions

Safety information for users is contained in the relative safety data sheet.

Empty containers or containers with traces of dried product film should be disposed of according to local regulations.

This product is alkaline (contains lime). Avoid any contact with skin and eyes. Wear safety glasses. In case of contact with eyes, rinse thoroughly with water. Seek medical attention if irritation persists.

FOR PROFESSIONAL USE ONLY

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424

RASA LIME

Viero

www.vieropaints.com
info@vieropaints.it

Product data sheet: VID455174T
Rev. 01 dated 31/07/2018

TECHNICAL/REGULATORY INFORMATION	APPLICABLE REGULATION	INFO AT 20 °C AND 60% HUMIDITY
Appearance in the can		Powder
Finish appearance		Matt
Fresh mortar density Kg/m ³	UNI EN 1015-6	1500 ÷ 1600
Water for mixing % by weight	UNI 8305	26 ÷ 29
Natural spread rate (Kg/m ²)	ISO 7254	1.5 - 2.0
Flash point °C	UNI 8909	Non-flammable
Shelf life (in a cool and dry place)	UNI 10154.	8 months
Overcoating Hours (h)		48
Application places		Interiors/Exteriors
Bases + achievable colours		White
Binder		Hydraulic
Tool cleaning		Water

FOR PROFESSIONAL USE ONLY

Toll Free Number: 800.219.420 (Italy)
International assistance: +39.0583.2424 (from other countries)

Mon - Fri [8:00 am/1:00 pm - 2:00 pm/5:30 pm]



cromology
Italia

COMPANY WITH
MANAGEMENT SYSTEM
CERTIFIED BY DNV GL
= ISO 9001 =
= ISO 14001 =
= OHSAS 18001 =

The information provided is based on our best technical and practical knowledge, but all advice and suggestions are given without any guarantee since the conditions of use are not under our direct control. In case of doubt, it is always advisable to carry out preliminary tests and/or to call our technicians.

Viero is a trademark of Cromology Italia S.p.A. - Via IV Novembre, 4 - 50016 Porcari (LU) VAT no.: 07684621001 - ITALY - Ph.: +39 0584 2424